

CANADIAN CARPET AND CUSHION

ENDURANCE PERFORMANCE UNDERCUSHION

Endurance is made from < 85% highest quality recycled rubber crumbs from tires. The product is mold and mildew resistant and it contains very low VOC's.

The product is easy to install and has excellent resistance to compression all while providing superior underfoot comfort.

It is particularly cherished for its sound deadening qualities and insulation properties.

ENDURANCE PERFORMANCE UNDERCUSHION →

PROPERTIES	METHOD	UNIT	ENDURANCE
SOUND INDEX	ASTM E413, E1007	FIIC	70
THICKNESS	---	mm	6
PAD WIDTH	---	m	54"
ROLL LENGTH	---	m	36'
BULK DENSITY	---	lb. /cu. ft.	22
ROLL AREA	---	sq. yd.	18
COMPRESSION SET	ASTM D3676 50% deflection, 22 hour	%	15% AT 23°C 25% AT 35°C 48% AT 70°C
COMPRESSION RESISTANCE	ASTM D3676	PERCENTAGE CHANGE IN THICKNESS WITH LOAD IN LB. PER SQUARE INCH (PSI)	AT 1 PSI - 5% AT PSI - 13% AT 6 PSI - 25% AT 12 PSI - 35% AT 30 PSI - 50% AT 60 PSI - /

